

ATION
USA
FILM
INHIBITOR-PATENT



HIGH PERFORMANCE VpCI™ PACKAGING

VpCI™-144, Patented Corrosion Inhibiting Paper



PRODUCT DESCRIPTION

Cortec VpCI-144 is the premium corrosion inhibiting paper in the industry. Our patented Vapor phase Corrosion Inhibiting technology has revolutionized the way metals are protected in an enclosed package. Cortec VpCI-144 paper provides superior corrosion protection for both ferrous and non-ferrous metals, which eliminates the need to inventory a variety of papers for all the different types of metal you need to protect.

Our VpCI-144 paper is coated with a water-based barrier coating. Historically, polyethylene and wax coatings have been used to seal porous paper to provide a moisture barrier and/or moisture-vapor barrier. When coated this way the resulting paper product is an environmental problem and cannot be recycled through normal channels. Cortec VpCI-144 paper provides an environmentally friendly alternative to polyethylene and wax paper.

Cortec VpCI-144 is environmentally safe, non-toxic, biodegradable, and fully recyclable/repulpable. That means VpCI-144 can be recycled into other types of paper products such as boxes, cardboard, and other corrugated materials. It also means that Cortec VpCI-144 can be "repulped" or made into or mixed with pulp to make new paper products.

Cortec VpCI-144 paper is made from the highest quality recycled neutral natural kraft paper: our paper is made without the use of any chlorine or other bleaching chemicals. This eliminates package

contamination found with other competing VCI/VPI papers. Parts protected with Cortec VpCI-144 can be painted, welded, and soldered. The thin protective film doesn't influence physical properties of most sensitive electrical and electronic components, including conductivity and resistivity. The paper basestock for the VCI/VPI coatings is produced with closely packed cellulose fibers which form a relatively non-permeable sheet. This attribute produces a uniform coating, as well as prevents the coating from striking through the paper.

TYPICAL APPLICATIONS

Cortec VpCI-144 paper can be used to protect products for storage and shipment in a wide variety of ways: end closures for shipping tubes, insert strips for recessed areas in large packages; and as sheet liners or separators between products.

The typical applications are:

- Metal production: coils, wire reels, plate, bar, etc.
- Metal forging and die casting: raw and machined forgings and castings.
- Metalworking: stamping, sheet metal work, springs, bearings, fasteners, tube, pipe, jewelry, silverware, etc.
- Finished products: engines, machinery, equipment, tools, hardware, appliances, instruments, motors, etc.
- Electrical and electronic: components, controls, printed circuit boards, etc.

FEATURES

- One product for all ferrous and non-ferrous metals.
- Biodegradable. Contains no nitrites, phosphates, silicones, chromates, or other heavy metals.
- Fully recyclable and repulpable according to TAPPI Useful Method 253 (modified)



- Effective against aggressive environments including humidity, SO₂, H₂S, and galvanic corrosion from dissimilar metals.
- Conforms to military specifications MIL-P-3420E.
- Protective film does not need to be removed prior to further surface finishing or coating application.
- Protects dry or oiled metals during storage, transit, and overseas shipment.
- Good moisture barrier and resistant to oils.
- Natural grade paper eliminates package contamination.
- Combines corrosion protection, barrier properties, and packaging into one step.

METHOD OF APPLICATION

Products should be packaged as soon after cleaning as possible. Keep the VpCl paper as close to the surface of the product as practical, leaving no barrier between the VpCl paper and the metal surface to be protected.

Use approximately 1 square foot (0.09 m²) of VpCl paper for every 3 square feet (0.28 m²) of surface to be protected, and 1 square foot (0.09 m²) of VpCl paper for every 0.5 cubic foot (0.01 m³) of void space. For long-term storage of up to ten years, enclose the wrapped product in an airtight package.

Standard construction of VpCl-144: Neutral natural paper coated on one side with the blend of water-barrier coating and VpCl material and with the barrier coating on the reverse side.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY SEALED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Galvanized Steel
- Cast Iron
- Aluminum Alloys
- Copper
- Brass (≤30% Zn)
- Solder

TYPICAL PROPERTIES

Property	TAPPI Method	Unit	Cortec
Basis Weight	T-410	lbs/3000ft ² (kg/m ²)	32.5 (158.69)
Caliper (thickness)	T-411	Inches (mm)	0.0032 (0.08125)
Tear-MD	T-411	gms	47.5
Tear-CD	T-411	gms	58.5
Dry Tensile-CD	T-494	lbs/in (kg/mm)	17.68 (0.315)
Dry Tensile-MD	T-494	lbs/in (kg/mm)	47.14 (0.8418)
TEA-CD	T-494	ft-lbs/ft (J/m ²)	3.6 (38.8)
TEA-MD	T-494	ft-lbs/ft (J/m ²)	1.9 (20.5)
Stretch-CD	T-404	%	4.26
Stretch-MD	T-404	%	1.47
Ink Float	T-530	seconds	15
Smooth-nonprint	T-538	sheffield	240
Smooth-VCI	T-538	sheffield	231
Internal Bond	T-541	ft-lbs/in (J/cm)	0.165 (0.064)
Abrasion-nonprint	T-476	gm loss/100 rev	0.007
Abrasion-VCI	T-476	gm loss/100 rev	0.002
WVTR (73°F, 50%RH)	ASTM E-96	Gms/ hour • m ²	0.147

CD = Cross Direction
MD = Machine Direction

PACKAGING AND STORAGE

Standard sizes: Converter rolls 48" x 26,000 feet (1.22 m x 7,925 m), roll stock 36" x 200 yards (0.91 m x 183 m), and 48" x 200 yards (1.22 m x 183 m).

Custom sizes also available.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet http://www.CortecVCI.com

printed on recycled paper  100% post consumer

Revised 2/13/08. Cortec Corporation 1998-2008. All rights reserved. Supersedes: 6/15/07

Cortec® is a trademark of Cortec Corporation

© 1998-2008, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited.

Distributed by: