



## VpCI™ HEAVY DUTY LUBRICANTS

# CorrLube™ VpCI™ Motor Oils



### PRODUCT DESCRIPTION

CorrLube™ Motor Oils are a high performance API certified oils for both gasoline and diesel engines. CorrLube™ Motor Oils provide superior corrosion protection and are highly recommended for use in any infrequently used vehicle or engine. Incorporated corrosion inhibitors provide dependable protection during storage conditions.

### CorrLube™ 10W-30

API certified SH\*, CH-4, CG-4 CF-4, CF-2, CF  
\* Exceeds 0.1% Phosphorous limit for API SJ

### CorrLube™ 15W-40

API certified SJ, CH-4, CG-4, CF-4, CF

### FEATURES

- Corrosion protection of ferrous and non-ferrous metals.
- High performance API certified.
- Available in 10W-30 and 15W-40 viscosity grades.
- For use in gasoline or diesel engines.
- Superior protection under continuous or intermittent use conditions.
- Continuous use prevents corrosive wear
- Continuous protection from moisture and acidic combustion by-products while equipment is in use or in storage



### TYPICAL APPLICATIONS

- Boats and yachts
- Show cars
- Motorcycles
- Military equipment
- Agricultural equipment
- Backup power generators
- Emergency vehicles
- Garden equipment
- Off road equipment
- Marine engines

### METALS PROTECTED

- Carbon steel
- Aluminum
- Brass
- Bronze
- Copper
- Tin
- Lead

### CHEMICAL AND PHYSICAL PROPERTIES 10W-30

SAE J300 (Typical)	
KV @ 100°C, cSt	11.5
CCS, cP @-20°C	3000
MRV TP-1 @-30°C	15,000
HTHS Viscosity, cP	3.4
Volatility (GCD) %@371°C	8
Flash Point, COC, C	233°
API Gravity	29.4
Total Base Number	8.1
Sulfated Ash, mass %	0.90
Total Acid Number	1.8



## 15W-40

SAEJ300 (Typical)	
KV @ 100°C, CST	16.0
CCS, cP @-15°C	3020
MRV TP-1@-25°C	15,200
HTHS Viscosity, cP	4.44
Volatility (GCD) %@371°C	5.2
API Gravity	29.4
Total Base Number	8.3
Sulfated Ash, mass %	0.92
Total Acid Number	1.85

### PERFORMANCE PROPERTIES AND TESTS

CorrLube™ is an ultra high performance motor oil with outstanding anticorrosion performance properties including:

- Dramatically improved protection of carbon steel and copper in condensing humidity atmosphere (ASTM D1748), and protection of carbon steel in accordance with the Ball Rust Test (inclusion in ASTM D4485) under acidic conditions.

### FOR INDUSTRIAL USE ONLY

**KEEP OUT OF REACH OF CHILDREN**

**KEEP CONTAINER TIGHTLY CLOSED**

**NOT FOR INTERNAL CONSUMPTION**

**CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION**

Time before corrosion			
Material	ASTM D1748		Ball Rust Test
	Carbon Steel	Copper	
Corr Lube™	20-25 days	>10 days	48 hours*
Castrol Diesel Oil	4-6 days	5-6 days	27 hours*
* The requirements are not less than 18 hours			

### OEM PERFORMANCE CLAIMS (MEETS OR EXCEEDS WITH THE APPROPRIATE GRADE):

- Mack EO-M Plus
- Mack EO-M
- Cummins 20076
- Cummins 20071
- Volvo VDS-2
- Volvo VDS
- Detroit Diesel Bulletin SE270
- Caterpillar Bulletin SEBU 6385
- Caterpillar Bulletin SEBU 6250
- Navistar Bulletin TSI-97 -12-03
- Allison C4 Quality
- Cat TO-2 Quality
- General Motors 9986155, 9986145
- Ford WFE-M2C906-A
- CID A-A-52306A

### PACKAGING AND STORAGE

CorrLube™ is available in 1 quart bottles (0.9464 liter), 1 gallon (3.78 liter) jug or can, 5 gallon (19 liter) plastic pail, 55 gallon (208 liter) metal drums, liquid totes and bulk. The shelf life of CorrLube™ is up to 24 months.

### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

**BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.** No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

**THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.**



4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com  
Internet <http://www.CortecVpCI.com>

printed on recycled paper 10% post consumer

Revised 01/15/02. Cortec Corporation 2002. All rights reserved. Supersedes: 6/13/01.  
CorrLube™ and VpCI™ are trademarks of Cortec Corporation.

Distributed by:

