

ATION
USA
FILM
HIBITOR-PATENT
INHIBITOR



HIGH PERFORMANCE VpCI® PACKAGING

EcoShield® Heat Sealable Paper



TYPICAL PROPERTIES

Property	TAPPI	Unit	EcoShield® N45 Paper
Basis Weight	T-410	lb/3,000 (g/m ²)	39±1 (64±2)
Base Stock	T-410	lb/3,000 (g/m ²)	37 (60)
Caliper	T-411	Mil (µm)	3.5±0.5 (89±12)
Brightness	T-452	%	92
Seal Strength	ASTM F88-99	lb/in (N/25.4mm)	1.2 ±0.3 (5.2±1.3)

DESCRIPTION

EcoShield® Heat Sealable Paper is a packaging product coated with a water based heat sealable adhesive coating. Seams formed from properly sealed product (heated with coated sides together) forms a bond stronger than the paper.

EcoShield® Heat Sealable Paper is fully repulpable and can readily be recycled.

TYPICAL APPLICATIONS

EcoShield® Heat Sealable Paper can be used to manufacture envelopes and bags. A heat seal temperature of ≥ 250°F (120°C) is recommended. Seal time may vary with specific sealing equipment.

FEATURES

- Fully recyclable (repulpable)
- Non-toxic, environmentally friendly
- Forms strong permanent bond between coated surfaces
- Printable

STANDARD TEST METHODS

TAPPI T-410	Basis Weight
TAPPI T-411	Caliper
TAPPI T-452	Brightness of pulp, paper, and paperboard
ASTM F88-99	Seal strength of flexible barrier materials

PACKAGING AND STORAGE

EcoShield® Paper is available in a 600' (182.88 meters) stock rolls, 36" or 48" wide (1-1.22 meters).

Custom sizes up to 68" wide (1.73 meters), and construction are available upon request.

**FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION**

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.cortecvci.com>

Printed on recycled paper  100% post consumer

Revised: 01/04/17. Supercedes: n/a. ©Cortec Corporation 2002-2016 of Cortec Corporation.
All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2016, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.