

MIGRATORY CORROSION INHIBITOR (MCI®) PRODUCTS FOR CONCRETE



MCI® Coating for Rebar



Uncoated

Coated

PRODUCT DESCRIPTION

MCI Coating for Rebar provides excellent protection in outside storage as well as offering excellent corrosion resistance for embedded rebars. This product is water based and environmentally friendly.

The recommended dry film thickness range is 0.5-2.0mils (12.5-50 microns). As a soft film, MCI Coating for Rebar is an excellent choice for long-term indoor protection (up to 5 years*) and short to medium-term (6-24 months*) unsheltered outdoor protection. The product cures to a soft film and eventually hardens. MCI Coating for Rebar has been tested for adhesion to concrete in accordance with ASTM A 775/A 775 M and showed positive results, confirming that MCI Coating for Rebar does not have to be removed prior to embedding in concrete (see Table 2).

*Depends on conditions and/or film thickness

FEATURES

- Excellent outdoor protection
- Multimetal protection
- Safe and easy to use
- Environmentally friendly
- Does not affect concrete adhesion to rebar
- Dilutable with water

TYPICAL APPLICATIONS

- Processing protection
- Overseas shipping
- Maintenance repairs
- Storage
- Protection for rebars embedded in concrete

PROPERTIES

Appearance	Off-white to beige viscous liquid
Dry to Recoat Time	30-90 minutes
Dry to Tacky Time	10-60 minutes
Dry to Cure Time	1-3 hours
Film Type	Soft, tacky
Non-volatile Content	27-33%
Shelf Life	12 months at 75°F (24°C)
Theoretical Coverage	265-345 ft ² /gal at 2-mil dry (undiluted) (28-34 m ² /l at 50 microns)
VOC	0.95 lb/gal (113 g/l)
Density	8.0-8.3 lb/gal (0.96-0.99 kg/l)
pH	9-10 (neat)

Table 1
Corrosion protection Properties

Test Method	DFT*	SAE 1010 Carbon Steel
ASTM D1748	1-mil (25 micron)	1000+ hr.
ASTM G 85-94	1-mil (25 micron)	600 hr.
ASTM B117	1 mil (25 micron)	200 hr.

*Dry Film Thickness

Table 2
Adhesion to concrete results (ASTM A 775/A 775M)

Test No	Pounds of Force*	
	Coated with MCI®-Coating for Rebar	Uncoated
1a	2,660 @ free-end	-----
1b	2,480 @ load-end	-----
1c	2,660 @ free-end	-----
2a	-----	2,600 @ loaded-end
2b	-----	2,670 @ loaded-end
2c	-----	3,040 @ loaded-end

*The data below indicates the smaller of the pounds of force required to move the embedded rebar either 0.002" as measured at the free-end or 0.010" at the loaded-end.



APPLICATION

Mix MCI Coating for Rebar prior to use. MCI Coating for Rebar can be used "as is" or diluted with water up to 50%, as long as a 1.0-2.0 mils (25-50 microns) dry film thickness is reached. It can be applied by spray, brush, roll or dip.

Airless Spray:

Pressure 2000 psi (140 bar)
Filter 60 mesh
Tip 0.015" (0.038 cm)

Conventional:

Equipment Binks 18 gun or equivalent
Automatization pressure 40 psi (3 bar)
Fluid pressure 20 psi (1 bar)
Cap/Tip 66/S

PRODUCT CLEANUP

Use soapy water to clean up tools and overspray.

LIMITATIONS

MCI Coating for Rebar should be completely dry before placing the part into storage.

PACKAGING AND STORAGE

MCI Coating for Rebar is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) metal drums, liquid totes and bulk. Do not allow product to freeze.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.cortecVCI.com>

printed on recycled paper  100% post consumer

Revised 7/12/07. Cortec Corporation 2001-2007. All rights reserved. Supersedes: 3/22/07.
MCI®, and Cortec® are a trademark of Cortec Corporation.