

VpCI®-395 Water Based Epoxy Primer

DESCRIPTION

VpCI®-395 is a fast drying, 2K water-based epoxy one coat system (primer) that can be applied DTM (Direct to Metal) and provides protection in harsh, outdoor, unsheltered applications. The complex mixture of non-toxic, organic inhibitors offers protection that competes with most paints and zinc-rich primers. Provides multi-metal protection. Excellent for immersion type conditions. Can be used as a topcoat for interior only applications (those not exposed to UV light). Can be matched to most custom colors. RAL 7046 is NSF 61 Approved.

PACKAGING & STORAGE

VpCI®-395 is available in 5 gallon (19 liter) kits, 4 gallons Part A, 1 gallon Part B. Keep product from freezing.

Product shelf life is 1 year.



CHARACTERISTICS/TECHNICAL DATA

Volume Solids	48.60%
Gloss (ASTM D532)	15-25
VOCs (ASTM D3960)	0.2 lbs/gal (24 g/l)
Viscosity	50-60 sec+Zahn#3
Pencil Hardness (ASTM D3363)	H
Spreading Rate	779 sq.ft/gal @ 1.0 mils DFT (mixed) (19.2 sq.m/l @ 25 µm)
Weight per Gallon	11.88 lbs/gal (1.42 kg/l)
Flash Point	122°F (50°C)
Recommended DFT	1.5-3.0 mils (37.5 – 75 µm)
Recommended WFT	3.0-6.0 mils (75-150 µm)
Dry to Touch	20-30 min
Dry to Handle	1-2 hrs
Recoat Time	Dry to touch - 72 hrs, sand thereafter
Force Dry	15-20 min @ 150°F (65°C)
Full Cure	3-7 days
Salt Spray (ASTM B117)	1000 hrs
Humidity (ASTM D1748)	500 hrs
Adhesion (ASTM D3359)	5B
Flexibility (ASTM D522)	1/2" mandrel (1.27cm)

*All tests performed after a 7 day cure at ambient temperature

VpCI®-395 Water Based Epoxy Primer

APPLICATION

Surface Preparation

Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, rust inhibitors, or any other surface contamination that could affect adhesion. For production line applications, use VpCI®-440 or similar phosphatizing pre-treatment. For structural steel applications, Cortec® recommends a minimum of a NACE #3/ SSPC-SP6 commercial blast clean. Consult Cortec® and/or test system adhesion prior to full scale application.

A wash primer such as VpCI®-373 green applied at 0.5-1.0 mils (12.5-25 microns) is recommended before applying the VpCI®-395 to aluminum, galvanized or plated substrates. When solvent based topcoats are applied over VpCI®-395, compatibility must be checked. **Note: Make sure dew point is more than 5°F (2°C) less than air temperature for application.**

Mix Ratio

White Base

4 Part - Part A 4 gal (15l)

1 Part- Part B 1 gal (3.8l)

Clear Base

3.5 Part - Part A 3.5 gal (13.25l)

1 Part - Part B 1 gal (3.8l)

Power agitate to a uniform consistency using a "squirrel cage" type mixer, hand-held drill mixer, or other equivalent method. VpCI®-395 can be applied by spray, roll, brush, or dip. When mixing using a pressure pot setup, allow 15-30 minutes of sweat-in time prior to application. Pot life is 2-3 hours.

Typical Equipment Set Ups

HVLP / Conventional Spray

Tip .009"-.021" *dependent upon pressures and viscosity

Air Pressure 45-55 psi

Fluid Pressure 10 psi

Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). Pot should always have dual regulation and be kept at same elevation as spray gun.

Air Assisted Airless / Airless

Tip .015"-.035" *dependent upon pressures and viscosity

Pressure 1800-2500 psi

Hose should be 3/8" (0.95 cm) I.D. minimum, but a 1/4" (0.64 cm) I.D. whip end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested.

Clean Up

Clean tools/equipment immediately after use with water when paint is still wet. When dry, use Butyl Cellulose or MEK. Follow mfg's safety recommendations when using any solvent.

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT SAFETY DATA SHEET FOR MORE INFORMATION



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC
info@cortecvci.com
http://www.cortecvci.com
http://www.corteccoatings.com



LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.