



HIGH PERFORMANCE VpCI® COATINGS

VpCI®-619

PRODUCT DESCRIPTION

VCI-619 is a water-based coating for high temperature (1,112°F/600°C) applications. A common and extremely useful application is the protection of steam or hot oil pipelines. This coating must be protected with either an insulation blanket or left in a non-disruptive area. The coating is light and powder-like once cured.

FEATURES

- Protects in wet and dry cycles
- Long lasting
- Excellent high temperature resistance
- Easy to apply
- Multimetal protection

TYPICAL APPLICATIONS

- Under pipe insulation
- Undisturbed areas
- Power plants
- Refineries
- Exhaust manifolds
- Ships

TYPICAL PROPERTIES

Appearance	White thixotropic liquid
Dry Time	20 minutes
Film Type	White powder
Non-volatile Content	18-22%
pH	8.2-8.7 (1% aqueous)
Shelf Life	24 months @ 75°F (24°C)
Theoretical Spread Rate	145-188 ft ² /gal @ 2 mils (4-5 m ² /l @ 50 microns)
Density	8.7-9.6 lb/gal (1.04-1.15 kg/l)

APPLICATION

Surface Preparation*:

NACE	SSPC	ARS
3	6	High B-1

Product Preparation:

VpCI-619 should be thoroughly mixed prior to use.

Product Application:

Normal wet film thickness of 6-8 mils (150-200 microns) yields 2-3 mils (50-75 microns) dry film thickness.

*SSPC - Steel Structures Painting Council

NACE - National Association of Corrosion Engineers

ARS - American Rust Standard Guide

STORAGE/PACKAGING

VpCI-619 is available in 5 gallon (19 liter) plastic containers, 55 gallon (208 liter) metal drums, liquid totes, and bulk. Do not allow product to freeze.



FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT SAFETY DATA SHEET FOR MORE
INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.cortecvci.com>

printed on recycled paper



100% post consumer

Revised: 8/28/13. ©Cortec Corporation 1998-2013. All rights reserved. Supersedes: 5/31/11.
©2013. Copying of these materials in any form without the authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.