

VpCI® METALWORKING PRODUCTS

VpCI®-327



ОПИСАНИЕ НА ПРОДУКТА

VpCI® -327 е готов за употреба инхибитор на корозия на масленна основата, който защитава по два оригинални начина.

Първо VpCI® - 327 образува слой върху металната повърхност който прилепва здраво към метала, в допълнение към този защитен слой, VpCIs изпаренията, са разтилат във въздуха над маслото, тези изпарения кондензират и формират защитна бариера на повърхностите без директен контакт с изделието. Комбинираното действие предоставя пълна защита на вътрешните части.

В допълнение VpCI® -327 е отличен продукт за премахване на пръстови отпечатъци от металната повърхност, който оставя почистената повърхност, защитена от ръжда. VpCI® - 327 е много икономичен, поради високото му повърхностно покритие.

ХАРАКТЕРИСТИКИ

- VpCI® - 327 Извършва ефективно защита дори при неблагоприятни условия с 100% относителна влажност на въздуха и при наличие на корозивни хлориди
- Водоотблъскващи свойства
- Отговаря на военен стандарт MIL-C-15074 E
- Отговаря на военен стандарт MIL-C-81309 E
- Не съдържа опасни хромати, нитрити, фосфати, сулфонати или калциеви съединения
- Високи проникващи свойства
- Използва най-добрите петролни дестилати, като носители
- Преминава през филтър с размер 1 микрон

ТИПИЧНИ ПРИЛОЖЕНИЯ

VpCI® -327 може да се използва за защита на алуминий, алуминиеви сплави, цветни метали, мед и сплавите му.

Устойчив слой с дебелина (по-малко от 20 микрона) сигурява защита от корозия до 24 месеца.

VpCI® -327 могат да се полагат чрез потапяне, пръскане или намазване на почти всички етапи на производството, съхранението или спедицията.

ЗАЩИТЕНИ МЕТАЛИ

- Черни метали
- Алуминий,
- Алуминиеви отливки
- Алуминиеви сплави
- Мед и медни сплави

ХАРАКТЕРНИ СВОЙСТВА

Външен вид	Леко жълта течност
Пламна температура	(71 ° C)
Не-летливи вещества	36- 47%
pH	8.5-9.5 (1% воден)
Плътност	(0.81-0.84 кг / л)

Пакетиране и съхранение

VpCI ® -327 се предлага в (19 литра) кофи, (208 литра) метални варели, и насипен вид. Срока на годност е **24 месеца** в плътно затворен съд.
Мин. температура на съхранение: **(-18 ° C)**
Макс. температура на съхранение: **(49 ° C)**

**САМО ЗА ПРОМИШЛЕННА УПОТРЕБА
ДА СЕ СЪХРАНЯВА НА МЯСТО ДАЛЕЧ ОТ ДЕЦА
ДА СЕ ДЪРЖИ ПЛЪТНО ЗАТВОРЕН
ДА НЕ СЕ КОНСУМИРА
ЗА ПОВЕЧЕ ИНФОРМАЦИЯ КОНСУЛТИРАЙТЕ ДАННИТЕ ЗА БЕЗОПАСНОСТ**

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.CortecVpCI.com>

printed on recycled paper  10% post consumer

Revised 3/31/06. Cortec Corporation 2002-2006. All rights reserved. Supersedes: 1/10/06.
Cortec® is a trademark of Cortec Corporation.

© 2002-2006, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited.

Distributed by:

CHIMTEC Ltd.
71 Vassil Droumev Str.
9000 VARNA
BULGARIA
Tel: +359 888 280 563
Email: deian_tachev@yahoo.fr

ХИМТЕК ООД
ул.Васил Друмев 71
9000 ВАРНА
Тел: 0888 280 563
Емаил: deian_tachev@yahoo.fr