

ATION
USA
FILM
INHIBITOR-PATENT
INHIBITOR



HIGH PERFORMANCE VpCI® PACKAGING

Cor-Pak® VpCI® Reinforced Paper Corrosion Inhibiting Paper



PRODUCT DESCRIPTION

Cor-Pak VpCI Reinforced Paper is the premium corrosion inhibiting reinforced paper in the industry. Our patented Vapor phase Corrosion Inhibiting technology has revolutionized the way metals are protected in an enclosed package. Cor-Pak VpCI Reinforced Paper provides superior corrosion protection for both ferrous and non-ferrous metals. Cor-Pak VpCI Reinforced Paper eliminates the need to stock a variety of papers for all the different types of metals and alloys you need to protect. Additionally, Cor-Pak VpCI Reinforced Paper is non-toxic and doesn't contain any nitrites, phosphates, silicates or other hazardous compounds.

Cor-Pak VpCI Reinforced Paper is made from the highest quality neutral natural kraft paper and has excellent tear resistance. It also offers a barrier to water, oil and grease. There are no chemical concentrations to calculate, no chemical tanks or application system to maintain. Just wrap your products in the paper, and fold edges together. Use adhesive tape as needed to hold paper folds in place. The VpCI coating on the paper vaporizes, reaching all metal surfaces to provide complete corrosion protection. The unique inhibiting action of the VpCI forms a very thin and very effective protective layer that does not alter the appearance of products or require removal.

Parts protected with Cor-Pak VpCI Reinforced Paper can be painted, welded, and soldered. The protective layer does not influence physical properties of most sensitive electrical components, including conductivity and resistance.

TYPICAL APPLICATIONS

Cor-Pak VpCI Reinforced Paper can be used to protect products for storage and shipment in a wide variety of ways: wrap for single item packaging or interleaving; end closures for shipping tubes; insert strips for recessed areas in large packages; and as sheet liners or separators between products. Cor-Pak VpCI Reinforced Paper is used in packaging of metals with pointed, odd shapes or sharp edges where puncture would be an issue with non-reinforced papers. It's also used in applications where damage to the item caused during shipping is a concern when using non-reinforced papers.

The typical applications are:

- Metals industry: coils, wire reels, plate, bar, etc.
- Metal forging and die casting: raw and machined forgings and castings.
- Metalworking: stamping, sheet metal work, springs, bearings, fasteners, tube, pipe, nails, etc.
- Finished products: engines, machinery, tools, hardware, appliances, instruments, motors, etc.
- Electrical and electronic components, controls, etc.

FEATURES

- Extremely durable paper allows you to ignore normal handling issues found in non-reinforced packaging papers.
- One product for all ferrous and non-ferrous metals.
- Non-toxic. Contains no nitrites, phosphates, silicones, chromates or other heavy metals.
- Effective against aggressive environments including humidity, SO₂, H₂S and galvanic corrosion from dissimilar metals.



- Conforms to military specifications MIL-P-3420E.
- Protective layer does not need to be removed prior to further surface finishing or coating application.
- Protects dry or oiled metals during storage, transit and overseas shipment.
- Natural grade paper eliminates package contamination.
- Combines corrosion protection and packaging into one step.

METHOD OF APPLICATION

Products should be packaged as soon after cleaning as possible, but completely dried of residual water. Keep the VpCl paper as close to the surface of the product as practical, leaving no barrier between the VpCl paper and the metal surface to be protected.

Use approximately 1 square foot (0.09 m²) of VpCl paper for every 3 square feet (0.28 m²) of surface to be protected, and 1 square foot (0.09 m²) of VpCl paper for every 0.5 cubic foot (0.01 m³) of void space. For long-term storage of up to ten years, enclose the wrapped product in an airtight package.

Standard Construction: Fiber glass reinforced polycoated neutral natural kraft paper, coated with VpCl material.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY SEALED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE

INFORMATION

TYPICAL PROPERTIES

Property	TAPPI Method	UNIT	Cor-Pak VpCl Reinforced Paper
Basis Weight lbs	T-410	lbs/3000ft ² (g/m ²)	70±5 (114±8 g/m ²)
Caliper (thickness)	T-411	Mils (μm)	9± 1 (230± 25)

TEST METHOD	RESULT
Impact Puncture ASTM D 3420-95B (J)	0.90

TEST METHOD	MD	CD
Tear Test ASTM 1-22-94A (%)	10.0	9.0

METALS PROTECTED

- Carbon Steel
- Stainless Steel
- Galvanized Steel
- Cast Iron
- Aluminum Alloys
- Copper
- Brass (≤30% Zn)
- Solder

PACKAGING AND STORAGE

Custom sizes and constructions available upon request.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:



4119 White Bear Parkway, St. Paul, MN 55110 USA
 Phone (651) 429-1100, Fax (651) 429-1122
 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
 Internet http://www.cortecvci.com