



**CORTEC**  
CORPORATION

Environmentally Safe VpCI®/MCI® Technologies

## EcoShield® 386 FD Water Based Micro Corrosion Inhibiting Coating

### DESCRIPTION

EcoShield® 386 FD is a fast drying, water-based acrylic one coat system (topcoat) that can be applied DTM (Direct to Metal) and provides protection in harsh, outdoor, unsheltered applications. The complex mixture of non-toxic, organic inhibitors offers protection that outperforms other paints and zinc-rich primers. This unique formula uses a complex mixture of nano sized non-toxic organic corrosion inhibitors which provide protection superior to traditional corrosion inhibiting coatings.

Provides multi-metal protection. Excellent UV resistance. Can be matched to most custom colors.

NSN 8030-01-481-8897 (clear only).

### PACKAGING & STORAGE

EcoShield® 386 FD is available in 5 gallon (19 L) pails, 55 gallon (208 L) metal drums, liquid totes, and bulk.

To ensure best product performance, store in original packaging, indoors, and out of direct sunlight at 40-100 °F (4-38 °C).

Shelf life: 1 year



### CHARACTERISTICS/TECHNICAL DATA

Volume Solids	31%
Gloss (ASTM D532)	80+
VOCs (ASTM D3960)	0.6 lbs/gal (72 g/L)
Viscosity	50-60 sec+ Zahn #3
Pencil Hardness (ASTM D3363)	HB-H
Spreading Rate	497 sq.ft/gal @ 1.0 mils DFT (12.2 sq.m/L @ 25 µm)
Weight per Gallon	8.58 lbs/gal (1.03 kg/L)
Flash Point	>200 °F (93 °C)
Recommended DFT	1.5-3.0 mils (37.5-75 µm)
Recommended WFT	4.8-9.6 mils (120-240 µm)
Dry to Touch	30 min
Dry to Handle	1 hr
Recoat Time	Dry to touch
Force Dry	5-10 min @ 150 °F (65 °C)
Full Cure	3-7 days
Salt Spray (ASTM B117)	1000 hrs
Humidity (ASTM D1748)	1000 hrs
Adhesion (ASTM D3359)	5B
Flexibility (ASTM D522)	½" mandrel (1.27cm)

# EcoShield® 386 FD Water Based Micro Corrosion Inhibiting Coating

## APPLICATION

### Surface Preparation

Substrate should be free of grease, oil, dirt, fingerprints, drawing compounds, rust inhibitors (except Cortec® approved), or any other surface contamination that could affect adhesion. For production line applications, use VpCI®-440 or similar phosphatizing pre-treatment. For structural steel applications, Cortec® recommends a minimum of a NACE #3/ SSPC-SP6 commercial blast clean. Consult Cortec® Technical Service and/or test system adhesion prior to full scale application.

A wash primer such as VpCI®-373 green applied at 0.5-1.0 mils (12.5-25 microns) is recommended before applying the EcoShield® 386 FD to aluminum, galvanized or plated substrates. Other recommended primers include VpCI®-375, 395 and 396 depending on coating requirements. When solvent based topcoats are applied over EcoShield® 386 FD, compatibility must be checked.

*Note: Make sure dew point is more than 5 °F (2 °C) less than air temperature for application. Power agitate to a uniform consistency using a "squirrel cage" type mixer, hand-held drill mixer, or other equivalent method. EcoShield® 386 FD can be applied by spray, roll, brush, or dip.*

### Typical Equipment Setups

#### HVLP / Conventional Spray

- Tip 0.02"-0.11" (0.5-2.8 mm)\* dependent upon pressures and viscosity
- Air Pressure 45-55 psi
- Fluid Pressure 10 psi
- Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). Pot should always have dual regulation and be kept at same elevation as spray gun.

#### Air Assisted Airless / Airless


- Tip 0.015"-0.035" (0.38-0.89 mm)\* dependent upon pressures and viscosity

- Pressure 1800-2500 psi
- Hose should be 3/8" (0.95 cm) I.D. minimum, but a 1/4" (0.64 cm) I.D. whip end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested.

### Cleanup

Clean tools/equipment immediately after use with water when paint is still wet. When dry, use Butyl Cellusolve or MEK. Follow mfg's safety recommendations when using any solvent.

### SALT SPRAY (ASTM B117) 1000 Hour Testing



*\*All tests performed after a 7 day cure at ambient temperature*

4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC  
info@cortecvci.com  
https://www.cortecvci.com  
https://www.corteccoatings.com



### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

**BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.** No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

**THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.**