

MIGRATORY CORROSION INHIBITOR (MCI®) PRODUCTS FOR CONCRETE



MCI®-2702

PRODUCT DESCRIPTION

MCI®-2702 is a single component, polymer-modified, cement-based mortar for structurally repairing deteriorated concrete. Developed with Sto Corporation, MCI®-2702 is designed for use on vertical or overhead surfaces for repairs from ¼ to 2 inches (6 to 51 mm) or apply it in lifts for deeper applications.

MCI®-2702 is a one-component vertical and overhead repair mortar that is ready to use; just add clean water. Once mixed by drill and paddle, it hangs 2 inches (51 mm) without falling, reducing waste and increasing job-site productivity.

MCI®-2702 provides the necessary concentration of MCI® (Migratory Corrosion Inhibitor) molecules on embedded steel bars. They create a protective monomolecular layer on metals embedded in concrete and inhibit further corrosion of bars.

The polymer in the product provides a creamy consistency that can be finished easily without tearing the surface. Finish it smooth with a trowel or textured with a sponge float or brush. Use MCI®-2702 for application depths from ¼ to 2 inches (6 mm to 51 mm) or apply it in lifts for deeper applications.

Features	Benefits
Polymer-modified	Increases durability and freeze-thaw resistance; excellent adhesion; improves flexural strength
Low shrinkage	Stable bond line; resists perimeter cracking
Thermally compatible with concrete	Prevents delamination caused by temperature changes
Integral Corrosion Inhibitor	Protects embedded steel against corrosion
High abrasion resistance	Wears longer; stands up to abusive traffic
One component	Factory-controlled polymer-to-cement ratio; ready-to-use; easily mixed with water on the job-site, no chemical jugs to dispose
Contains Migrating Corrosion Inhibitor (MCI)	Seeks out and forms a corrosion inhibiting protective layer on metals; migrates to adjacent areas to protect metals around the repair area; reduces the halo or ring effect surrounding the repair area

SURFACE PREPARATION

Remove loose and deteriorated concrete by mechanical chipping or sandblasting to obtain a fractured aggregate surface. Detail the edge of the patch to a 90° angle to eliminate feather edging. Make sure surfaces are sound, clean, and free of all bond-inhibiting materials including oil, dirt, dust, laitance and standing water.

MIXING

Use MCI®-2702 at a preconditioned temperature of 70 ± 5°F (21 ± 3°C).

Use 6.0 to 6.5 pints (2.83 to 3.08 L) of water per 56-pound (25 kg) bag.

Mixing must be achieved mechanically using a slow-speed, ¾ inch (19 mm) drill and mixing paddle. Pour 6.0 pints (2.83 L) of water into a clean 5 gallon (19 L) mixing bucket. Mix while slowly adding the powder, one-third at a time. If more water is needed, up to one-half pint (.24 L) may be added.

Mix up to 4 minutes, to a uniform, lump-free consistency. Avoid overmixing, which could entrap air. Once mixed, the working time is 25-45 minutes, depending upon material, ambient and surface conditions.

LIMITATIONS

- Apply only when the surface and ambient temperature are 45-50° F (7-10°C) and rising. See Cold Weather Application guidelines, per ACI, for applications in temperatures less than 50° F (10°C). Applications made during temperatures greater than 85°F (29°C) should follow Hot Weather Application guidelines, per ACI.
- The minimum required thickness is 1/4 inch (6 mm).
- Application depths greater than 2 inches (51 mm) must be completed in lifts.
- Do not add more water than specified.
- Do not add additional powder from other units.
- Do not overmix.



CORTEC
CORPORATION

Environmentally Safe VpCI™/MCI® Technologies

APPLICATION

Apply only to sound and clean, properly prepared, frost-free surfaces. Dampen the area to be repaired so that the pores of the concrete are filled with water. Remove any ponding or glistening water on the surface (saturated surface dry/SSD). **IMPORTANT:** Work a scrub coat of the mixed material into the substrate to ensure intimate contact and establish bond.

Complete the repair while the scrub coat is still wet and trowel to the desired finish. MCI-2702 can be applied to a thickness of 2 inches (51 mm) in one lift. For application depths greater than 2 inches (51 mm) apply MCI®-2702 in successive lifts.

For more lifts, scarify the first lift and allow it to set until hardened sufficiently to accept the next lift, about 30 minutes at 75°F (23°C). Trowel the final lift to the desired finish.

Curing

Direct sun or wind may cause unwanted rapid surface drying. Curing may be accomplished by continuous water fogging for 48 hours or cover with damp burlap or burlene curing blankets. Do not use solvent-based curing compounds. If a coating or sealer will be applied, use water fogging or blanket curing methods and prep finished surface per manufacturer's recommendations.

Clean Up

Clean tools and equipment with water immediately after use. Cured material can only be removed mechanically.

YIELD

0.43 ft³ per 56 lb bag (0.012 m³ per 25 kg bag).

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

COVERAGE

20-25 ft² per 50 lb bag, applied at ¼ inch thick (2 m² per 23 kg bag, at 6 mm thick).

TECHNICAL DATA

Report	Test Method	Criteria	Test Results
Working time (minutes)			15-30
Compressive Strength (psi/Mpa)	ASTM C-109	1 day	3,000+/20.7
		7 days	5,000+/34.5
		28 days	7,000+/48.3
Flexural Strength (psi/Mpa)	ASTM C-293	7 days	1,100+/7.59
		28 days	1,500+/8.97
Modulus of Elasticity in Compression (psi/Mpa)	ASTM C-469	28 days	2.26 x 10 ⁶ / 1.56 x 10 ⁴
Splitting Tensile Strength (psi/Mpa)	ASTM C-496	7 days	485/3.35
		28 days	565/3.90
Shrinkage (%)	ASTM C-157	7 days	<.1
		28 days	<.1
Direct Tensile Bond (psi/Mpa)	ASTM D-4541	28 days	500
Length Change	ASTM C-157	28 days	<0.03*

Typical values for material cured at 73°F (23°C) and 50% R.H.

* Wet Cure

PACKAGING AND STORAGE

MCI®-2702 is available in 56 lb bag (25 kg). The shelf life of the product is 12 months in original, unopened, properly stored container. Store in a dry area between 50°F (10°C) and 85°F (29°C). Protect from direct sunlight and extreme heat.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.CortecVCI.com>

printed on recycled paper  100% post consumer

Revised 4/09/07. Cortec Corporation 2003-2007. All rights reserved. Supersedes: 11/01/06.
MCI® is a trademark of Cortec Corporation.

Distributed by: