



VpCI® METALWORKING PRODUCTS



VpCI®-329 D



OPIS PROIZVODA

VpCI®-329 D je proizvod na bazi otapala, spreman za upotrebu odmah bez dodatne pripreme. VpCI®-329 D omogućuje odličnu zaštitu metala u zatvorenom i otvorenom natkritom skladištu.

VpCI®-329 D štiti na dva jedinstvena načina:

Prvo, inhibitori korozije topivi u ulju zajedno sa uljem stvaraju čvrsti sloj koji prijanja na metalnu površinu, pružajući odličnu zaštitu od korozije.

Pored uljnog filma na metalnoj površini, VpCI®-329 D sadrži hlapljive inhibitore korozije koji se elektrokemijski vežu na metalnu površinu.

VpCI®-329 D je izvrstan za zaštitu metalnih dijelova koji zahtijevaju lagani premaz ulja za daljnju obradu i otpremu, kao što su zupčanci, vretena, zavojnice ili bilo koji drugi metalni dio koji koristi ulje za zaštitu od korozije.

VpCI®-369D na bazi bio ulja dostopan je u verziji ES (easy to spray), za alpiciranje ručnom prskalicom.

KARAKTERISTIKE

- Djeluje učinkovito i u nepovoljnim uvjetima 100% relativne vlažnosti i u prisutnosti korozivnih utjecaja klorida, vodikov sulfida ili drugi sumpornih spojeva

- Visoka točka zapaljivosti i sigurnost od požara
- Ne sadrži opasne kromate, nitrite ili fosfatne inhibitore
- Osigurava univerzalnu zaštitu od korozije obojenih i nebojenih metala
- Termalno stabilan, omogućuje dugotrajnost kontakt sa metalnom površinom i zaštitu od korozije
- VpCI®-329 D je posebna verzija VpCI®-329 koja je razrijeđena 1:9 i spremna za upotrebu

NAČIN PRIMJENE

VpCI®-329 D može se primjenjivati prskanjem, uranjanjem, valjkom ili četkom.

VpCI®-369D ES može se lagano alpicirati ručnom prskalicom.

TIPIČNA SVOJSTVA

VpCI®-329 D

Izgled	tamna do neprozirna žuta uljasta tekućina
Nosač	lagano ulje
Pokrivenost	24-36 m ² / l
Vrijeme sušenja	Ostaje ljepljivo
Debljina filma (suhi film)	25-37,5 mikrona
Vrsta filma	ulje
Točka zapaljivosti	146°C
Sadržaj nehlapljivih čestica	87-97%
Miris	nafta
Postupak odstranjivanja	Naftna otapala/alkalno odmašivači (VCI-410 Cortec serija)
Gustoća	0,89-0,91 kg/l



VpCI®-329 D ES

Izgled	tamna do neprozirna žuta uljasta tekućina
Nosač	Kanola ulje i mineralno otapalo
Točka zapaljivosti	115 °C
Postupak odstranjanja	Naftna otapala/alkalni odmašćivači (VCI-410 Cortec serija)
Gustoća	0,84-0,90 kg/

PACKAGING AND STORAGE

VpCI®-329 D i VpCI®-329 D ES pakirani su u plastične posude od 5 galona (19 litara), 55 galon (208 l) metalne bačve, kontejneri za tekućine 1020 l.

VpCI®-329 D i VpCI®-329 D trebaju biti pohranjen u originalnom pakiranju i zatvoreni. Prije svake upotrebe dobro promješati. Rok trajanja je 24 mjeseca u zatvorenim originalnim posudama.

PAKIRANJE I SKLADIŠTENJE

ASTM D-1748	Vlažna komora	400+ Sati
-------------	---------------	-----------

SAMO ZA INDUSTRIJSKU UPORABU

ČUVATI DALJE OD DOHVATA DJECE

DRŽATI BAČVE DOBRO ZATVORENE

PREGLEDATI SIGURNOSNO TEHNIČKI LIST O PROIZVODU PRIJE UPORABE

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.
BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



CORTEC
CORPORATION

® Environmentally Safe VpCI®/MCI® Technologies

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
<http://www.cortecvci.com>

Printed on recycled paper  100% post consumer

Revised: 07/20/17. Supersedes: 11/16/15. ©Cortec Corporation 2002-2017 of Cortec Corporation.
All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2017, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

Distributed by: