



VpCI®-380 Railcar Coating



PRODUCT DESCRIPTION

VpCI-380 Railcar Coating is a unique, direct to metal (DTM), fluoropolymer modified water-based acrylic. Designed specifically for the railcar industry, the coating also demonstrates excellent adhesion to a wide variety of substrates including ferrous and non-ferrous metals and certain engineered plastics. The complex mixture of nontoxic, organic inhibitors offer protection that can compete with most primer / topcoat systems.

VpCI-380 provides a fast-drying thixotropic coating that exhibits alkyd-like gloss, flow, and leveling properties with good resistance to sag. The hardness and moisture resistance properties make it an excellent choice for air-dry / force-dry industrial finishes. It gives optimal outdoor performance without cracking or chipping upon prolonged exposure to sunlight.

FEATURES

- Fast-drying / high gloss
- Non-flammable
- UV resistant when dried
- Optimal outdoor performance
- Can be used as one coat system (primer & topcoat)
- Provides multimetal protection
- Good adhesion to ferrous and non-ferrous metals
- Adhesion to some engineered plastics

METALS PROTECTED

- Carbon steel
- Aluminum**
- Stainless steel
- Galvanized steel**

** A wash primer such as VpCI-373 green applied at 0.5-1.0 mils (12.5-25 microns) may be necessary before applying the VpCI-380 to these substrates. A test area for adhesion is recommended.

CORROSION RESISTANCE DATA*

	Dry Film Thickness Mils (Microns)	Hours to Failure
ASTM B-117 (Salt-spray)	4.0-4.5 (100.0-112.5)	1000 +
ASTM D1748 (Humidity)	4.0 - 4.5 (100-112.5)	1000 +
ASTM D870 (Water Immersion) Adhesion		300 hours 5B after 24 hours of recovery

TYPICAL PROPERTIES*

Appearance	Liquid, various colors
Density	8.5-9.5 lb/gal (1.01-1.14 kg/l)
Non-volatile Content	37-43%
Dry Film Thickness (per coat)	3.0-5.0 mils (75-125 microns)
Theoretical Spread Rate	168-112 ft ² /gal (3-5 mils) (4.12-2.75 m ² /l) (75-125 microns)
Dry to Touch Time	30 minutes @ 77°F (25°C) at 3 mils (75 microns) DFT
Fully Cured	7 days@77°(25°C) 55% RH
Temperature Stability	45°-90°F (7°-32°C)
VOC (ASTM D-3960)	1.6-1.7 lb/gal (0.7-0.8 g/l)
Viscosity	800-4,000 CPS @ 77°F (25°C)**
Gloss (ASTM D532)	80+
Pencil Hardness	H-2H(ASTM D3363)
Adhesion (ASTM D3359)	5B
Flexibility (ASTM D522)	1/2" 180°bend



APPLICATION

When VpCI-380 is applied in 3-5 mil DFT, it can be used as a topcoat and primer. VpCI-380 can also be used as a topcoat with Cortec's VpCI-395 primer.

Note: Make sure dew point is more than 5°F (2°C) less than air temperature for application.

Power agitate to a uniform consistency using a "squirrel cage" type mixer, hand-held drill mixer, or other equivalent method.

VpCI-380 can be applied by spray, flow coat, brush, or dip.

Conventional Spray

Manufacturer	Gun Model	Tip/Aircap Combination
DeVilbiss	MBC or JGA	704E
Binks	#18 or #62	66PE

Fluid hose should be 3/8" (0.95 cm) I.D. with a maximum length of 50 feet (15.2 m). Pot should always have dual regulation and be kept at same elevation as spray gun.

Airless

Manufacturer	Gun Model	Tip/Aircap Combination
Graco	205-591	Bulldog
Binks	Model 500	Mercury 5C
DeVilbiss	JGN-501	QFA-519

Hose should be 3/8" (0.95 cm) I.D. minimum, but a 1/4" (0.64 cm) I.D. whip end section may be used for ease of application. A maximum length of 100 feet (30.5 m) is suggested. Best results will be obtained using a 0.013"-0.017" (0.3-0.4 cm) tip at 1200-1700 psi (83-117 bar).

Note: Nylon or Teflon type packings are available from pump manufacturer and are highly recommended.

Note: Similar equipment may be suitable.

PACKAGING AND STORAGE

VpCI-380 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) metal drums, liquid totes, and bulk. Keep product from freezing. Product shelf life is 1 year.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT SAFETY DATA SHEET FOR MORE

INFORMATION

*All tests performed after a 7 day cure at ambient temperature.

**Viscosity can be set per customer request.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.


BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@corotecvci.com
Internet <http://www.corotecvci.com>

Distributed by:

printed on recycled paper  100% post consumer
Revised: 8/26/13. ©Cortec Corporation 2011-2013. Supersedes: 3/13/12. Cortec® is a trademark of Cortec Corporation. © 2013, ©Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.