

## MCI®-2026 Floor Coating Chemical Resistance Guide

No warranty is expressed or implied regarding this information. Specific results obtained by the customer are affected by conditions which are beyond Cortec's control. Therefore, it is recommended that customers perform their own tests to determine product suitability for a particular purpose.

1. Excellent Resistance
2. Good Resistance
3. Fair Resistance
4. Occasional Spills are Acceptable
5. Not Recommended for Contact
6. Has Not Been Tested

### ACIDS - ORGANIC

Chemical	Resistance Rating
Acetic Acid 5%	1
Acetic Acid 10%	1
Acetic Acid, Glacial	1
Benzoic Acid	1
Butyric Acid 10%	1
Citric Acid 50%	1
Diglycolic Acid	1
Fatty Acid	1
Formic Acid <10%	1
Formic Acid >10%	2
Lactic Acid <20%	1
Lactic Acid 25%	1
Maleic Acid 30%	1
Maleic Acid 60%	1
Malic 50%	1
Monochloro Acetic 5%	1
Monochloro Acetic 10%	2
Oleic Acid	1
Oxalic Acid	1
Phthalic Acid	1
Succinic Acid	2
Tannic Acid, Sat.	1
Tartaric Acid, Sat.	1

# MCI®-2026 Floor Coating Chemical Resistance Guide

## ACIDS - INORGANIC

Chemical	Resistance Rating
Boric Acid 30%	1
Chromic Acid 10%	1
Chromic Acid 20%	1
Fluoboric Acid	1
Hydrochloric Acid 15%	1
Hydrochloric Acid 37%	1
Hydrofluoric Acid 5%	1
Hydrofluoric Acid 15%	2
Hypochlorous Acid 5%	1
Nitric Acid 10%	1
Nitric Acid 20%	1
Nitric Acid 30%	1
Nitric Acid >40%	2
Phosphoric Acid <50%	1
Phosphoric Acid 70%	1
Phosphoric Acid, Conc.	1
Sulfuric Acid 20%	1
Sulfuric Acid 50%	1
Sulfuric Acid 70%	1
Sulfuric Acid 98%	1

## SOLVENTS - CHLORINATED

Chemical	Resistance Rating
Ethylene Dichloride	2
Methylene Chloride	5
Perchloroethylene	1
Trichloroethane	1
Trichloroethylene	5

## SOLVENTS - AROMATIC AND ALIPHATIC

Chemical	Resistance Rating
Benzene	2
Chlorobenzene	1
Gasoline	1
Mineral Spirits	1

Naphtha	1
Naphthalene	1
Toluene	1
Xylene	1

## ALCOHOLS

Chemical	Resistance Rating
Cyclohexanol	1
Diacetone Alcohol	1
Ethylene Glycol	1
Glycerine	1
Isopropyl Alcohol	1
Methyl Alcohol	2
Phenol 5%	3
Triethylene Glycol	1

## KETONES - ESTERS

Chemical	Resistance Rating
Acetone	1
Amyl Acetate	1
Butyl Acetate	1
Cyclohexanone	2
Ethyl Acetate	2
Methyl Ethyl Ketone	3
Methyl Isobutyl Ketone	3
Methyl Salicylate 50%	3

## ALKALIES AND SALTS

Chemical	Resistance Rating
Ammonium Hydroxide <20%	1
Ammonium Hydroxide >40%	2
Ammonium Nitrate, Sat.	1
Ammonium Persulfate	1
Ammonium Persulfate, Sat.	1
Calcium Chloride 50%	1
Calcium Hypochlorite <15%	1
Ferric Chloride	1

# MCI®-2026 Floor Coating Chemical Resistance Guide

Ferrous Sulfate	1
Potassium Hydroxide <40%	1
Sodium Benzoate	1
Sodium Bicarbonate, Sat.	1
Sodium Bisulfate, Sat.	1
Sodium Bisulfite, Sat.	1
Sodium Chloride, Sat.	1
Sodium Hydroxide 50%	1
Sodium Hypochlorite 10%	1
Sodium Propionate	2
Sodium Sulfate, Sat.	1
Sodium Sulfide, Sat.	1
Trisodium Phosphate	1

## OILS

Chemical	Resistance Rating
Corn Oil	1
Cutting Oils	1
Linseed Oil	1
Mineral Oils	1
Vegetable Oils	1

## MISCELLANEOUS

Chemical	Resistance Rating
Acrylonitrile	3
Aluminum Chloride <50%	1
Aluminum Chloride >50%	1
Aniline	2
Beer	1
Butyl Lactate	1
Bromine	1
Carbon Disulfide	5
Carbon Tetrachloride	1
Chloroform	5
Copper Fluoroborate	1
Cyclohexane	1
Diethyl Phthalate	1
Ether	1

Formaldehyde	1
Glutamate	1
Glyoxal	1
Hydrogen Peroxide 10%	1
JP5 Jet Fuel	1
Juices, Fruit	1
Juices, Vegetable	1
Kerosene	1
Lanoline	1
Lard	1
Mayonnaise	1
Milk	1
Mustard	1
Peanut Butter	1
Pyridine	5
Skydrol	1
Sucrose Sol. Sat.	1
Triacetin	1
Triethanolamine	1
Urea	1
Vinegar	1
Water	1
Wine	1
Zinc Nitrate	1

# MCI®-2026 Floor Coating Chemical Resistance Guide

4119 White Bear Parkway, St. Paul, MN 55110  
Phone (651) 429-1100  
Toll Free (800) 4-CORTEC  
productinfo@cortecvci.com  
www.cortecvci.com  
www.cortecmci.com



### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

**BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH.** No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

**THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.**