



MCI® Construction Film

DESCRIPTION

MCI® Construction Film is a blue colored polyethylene film designed for use in the construction industry. Unlike conventional plastic films used for interleaving, vapor barriers, etc., MCI® Film contains technology to inhibit corrosion of both ferrous and non-ferrous metals. In areas where conventional films are used, metal parts that come in contact with the film are susceptible to corrosion. The technology incorporated into MCI® Film inhibits corrosion on metal parts and structures it is used with.

PACKAGING & STORAGE

MCI® Construction Film is available in an 4 mil gauge ranging in widths from 3" to 32' (7.6 cm-9.75m). Contact Cortec® for minimum quantities and specific sizes. Stock size is 20'x100' (6.1m-30.5m) Shelf life is 2 years.



HOW IT WORKS

MCI® Construction Film is an excellent replacement for conventional polyethylene sheeting used in the construction industry. It does not contain free amines, phosphates, or halogens. MCI® Construction Film is also non-toxic and 100% recyclable.

Not only does MCI® Construction Film inhibit corrosion on metallic surfaces that it is in contact with, it also protects other metal parts via vapor phase inhibitors. These inhibitors migrate through the air to reach and protect metal surfaces that are not in direct contact with MCI® Construction Film. When MCI® Construction Film is used between concrete and metal studs it not only stops the corrosion that can occur at the contact points, it also protects the rest of the stud, adding to the life of the structure.

WHERE TO USE

- Carbon steel
- Stainless steel
- Galvanized steel
- Aluminum and alloys
- Copper and alloys
- Zinc

ADVANTAGES

- Provides multimetal protection
- Void spaces and recessed areas are protected
- Economical
- Provides UV protection
- High puncture and tear resistance
- Good moisture barrier
- Recyclable

PHYSICAL PROPERTIES

Property	Test Method	Units	Value*
Thickness	ASTM D6988	mil	4.00
Breaking Factor	ASTM D882-02	lbs/in	18/19
Tensile Strength at Break	ASTM D882-02	psi	44423/4357
Elongation at Break	ASTM D882-02	%	778/835
Yield Strength	ASTM D882-02	psi	1334/1610
Tear Strength	ASTM D19222-06a	mN	11160/15413
Puncture Resistance	MIL-STD-3010B	lbf	6.02
Dart Drop Impact Resistance	ASTM D1709-04, Test Mehod A	grams	791

*Machine direction/cross direction

4119 White Bear Parkway, St. Paul, MN 55110
Phone (651) 429-1100
Toll Free (800) 4-CORTEC
productinfo@cortecvci.com
www.cortecvci.com
www.cortecmci.com



LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.